

When protection & safety must be **Absolutely Assured**



RADIATION SHIELDING **LEAD GLASS**

LX-57B Radiation Shielding

DESCRIPTION:

MarShield's LX-57B x-ray shielding lead glass is made of high quality optical grade material. It provides excellent radiation shielding, superb visual clarity, high light transmission and does not discolour due to radiation. The hard, polished surfaces have excellent scratch resistance. LX-57B is available in thicknesses of 7mm, 9mm, 14mm, and 17mm.

FEATURES AND BENEFITS:

- Stock sizes are available up to 48" X 96". Available upon special request is 48"X 102"



STANDARD SIZES (IN INCHES)	
8X10	20X24
10x10 10x12	24x41 24x30 124x36 124x28
12x12 12x16 12x18 12x20	30x30 1 30x36 1 32x40
12x24 114x18	36x61 36x48 36x60 1 36x72 1 36x84 36x66
16x20 1 16x24	42x48 142x60 1 42x72 142x84 1 42x96
18x24 1 18x26	48x48 148x60 1 48x72 148x84 1 48x96

Note: 24-Hour Turnaround Time Is Available On Most Sizes



STANDARD LEAD GLASS

LX-57B Radiation Shielding

LX-57B is available in the following thicknesses and lead equivalencies:

THICKNESS	7mm	9mm	14mm	17mm
Lead Equivalent (in)	1/16"	*5/64"	*7/64"	*1/8"
Lead Equivalent (mmPb)	1.6	2.0	3.0	3.3
X-Ray Tube Peak (kV)	150	150	200	200
Weight (lbs/ft ²)	6.5	8.1	13.1	14.8
Laminated	No	No	Yes (7mm + 7mm)	Yes (7mm + 9mm)

*Lead Equivalent is guaranteed in (mmPb). The converted fraction (in.) is less than the lead equivalent (mmPb); fraction is over-coverage

To calculate the values Of the range of "Lead Equivalent (lbs/ sq.ft.)", we converted from the values Of the range of "Lead Equivalent (mmPb)" using the mentioned figures and rounded Off the fractions to one decimal place: 1 f00t=30.48cm / 1 pound=453.59g / Density Of Resistant to discolouration due to exposure to ultraviolet rays or cleaning chemicals. The durable LX-57B glass retains its appealing visual clarity. Offers excellent light transmission (87.3% with 7mm thick glass). LX-57B is non-combustible and will not emit toxic fumes when being cut.

Both surfaces of LX-57B are polished. Using Mohr's hardness scale, LX-57B tests at level 6 (comparable to feldspar, a constituent of granite). LX-57B has excellent scratch resistance because of its hard surface.


LX-57B is a lead barium type glass of high quality optical grade with over 60 percent heavy metal oxide, including at least 55 percent PbO.

PROPERTIES OF 7mm, 9mm, 14mm, 17mm LX-57B

- Minimum density: 4.36 (g/cm³)
- Refractive index (Nd): 1.71
- Thermal expansion coefficient: 80 x 10⁻⁷/OC (30-380 O C)
- Knoop hardness: 370

LX-57B LEAD GLASS VS. LEAD ACRYLIC/PLASTIC:

For the Same Lead Equivalent*



1.800.381.5335 | sales@marshield.com | www.marshield.com

LEAD LINED STORAGE CONTAINERS • MODULAR RADIATION BARRIERS & WALLS • MODULAR X-RAY ROOMS • ROLLING RADIATION BARRIERS • SHEET LEAD



STANDARD LEAD GLASS

LX-57B Radiation Shielding

RELATIVE THICKNESS

For the same lead equivalent, acrylic/plastic has to be approximately five times thicker than LX-57B lead glass - significantly reducing observation capabilities. For example, at 16mm Pb, lead glass would be 5/16" thick. Acrylic/plastic would be approximately 1-112" thick for the same protection. The extra thickness of acrylic/plastic may require special framing. LX-57B fits standard sized frames.

APPLICATIONS

Medical

X-ray rooms, operating theatres, radiation therapy rooms, dental clinics, veterinary clinics, laboratories, medical diagnostics screens, and eye protection lenses.

Industrial

Airport luggage inspection equipment and radiation testing equipment for industrial products.

Nuclear

Radioactive storage stations, nuclear fuel development and reprocessing plants, and applications near nuclear reactors.

COMPARISON TABLE	LX-57B LEAD GLASS	LEAD ACRYLIC/ PLASTIC SHEET	BEST PRODUCT
Combustible	No	Yes	LX-57B Lead Glass
Effect of Water Absorption	None	Effects Length & Thickness	LX-57B Lead Glass
Installation	Standard	Requires Special Care	LX-57B Lead Glass
Light Transmission (1.6mm Lead Equiv., at 150kV)	87.3%	59.5%	LX-57B Lead Glass
Thickness (1.6mm Lead Equiv., at 150kV)	7mm	42mm (6 times thicker)	LX-57B Lead Glass
Weight	6.5 lbs/ft ²	14 lbs/ft ²	LX-57B Lead Glass
Effects of Sun	None	Causes Cracking	LX-57B Lead Glass
Chemical Resistance			
a) Acid	Greater	Less	LX-57B Lead Glass
b) Alkali	Greater	Less	LX-57B Lead Glass

1.800.381.5335 | sales@marshield.com | www.marshield.com

LEAD LINED STORAGE CONTAINERS • MODULAR RADIATION BARRIERS & WALLS • MODULAR X-RAY ROOMS • ROLLING RADIATION BARRIERS • SHEET LEAD



SAFETY LEAD GLASS


Saf-T-Lite Radiation Protector

DESCRIPTION:

MarShield's Saf-T-Lite Radiation Protector glass comprises LX-57B lead glass, an interlayer, and float glass in a laminated sandwich to create a durable, shatter-resistant alternative to lead acrylic/plastic. This lead safety glass is commonly used in our mobile radiation shields and modular radiation barriers.

FEATURES AND BENEFITS:

- Interlayer Saf-T-Lite lead safety glass is available only in 1 mm thickness (16mm lead equivalency)
- Provides excellent light transmission of 878%
- Weight: 8 lbs. per sq. ft.
- Meets or exceeds the high standards of stringent safety regulations established in the medical, scientific, as well as nuclear fields around the world, including ANSI Z97.1-1984 and 16 CFR 1201 Cat. II.



1.800.381.5335 | sales@marshield.com | www.marshield.com

LEAD LINED STORAGE CONTAINERS • MODULAR RADIATION BARRIERS & WALLS • MODULAR X-RAY ROOMS • ROLLING RADIATION BARRIERS • SHEET LEAD



SAFETY LEAD GLASS


LX Premium Radiation Shielding

DESCRIPTION:

LX Premium is the next generation of radiation shielding glass. It has a multilayer structure, manufactured by inserting LX-57B high-lead glass between panels of protective sheet glass. This results in a glass surface that will not stain or discolour, even in contact with chemicals or if it is wiped with a wet cloth.

FEATURES AND BENEFITS:

- High transparency — glass will not stain or discolour when lead substances react to moisture or lipids
- Provides excellent light transmission (at 550nm) Of more than 80%
- Easy to maintain — glass can be using such items as a wet cloth, glass cleaners, and detergents without any concern about fogging staining or discolouration. You would clean LX Premium the same way you would clean ordinary windowpanes
- Multilayer laminated glass is impact-safe and shatter resistant



Available in the following thicknesses and lead equivalencies:

THICKNESS	12mm	14mm	20mm	22mm
Lead Equivalent (in)	1/16"	*5/64"	*7/64"	*1/8"
Lead Equivalent (mmPb)	1.6	2.0	3.0	3.3
X-Ray Tube Peak (kV)	150	150	200	200
Weight (lbs/ft ²)	8.8	10.4	15.5	17.0

**Lead Equivalent is guaranteed in (mmPb). The converted fraction (in.) is less than the lead equivalent (mmPb); fraction is over-coverage.*

To calculate the values of the range of "Lead Equivalent (lbs/sq.ft.)", we converted from the values of the range of "Lead Equivalent (mmPb)" using the mentioned figures and rounded off the fractions to one decimal place: 1 foot = 30.48cm / 1 pound = 453.59 g/Density of lead = 11.39g/cm³. Thickness tolerance can be up to +/- 1.3mm.

Properties - 12mm, 14mm, 20mm, 22mm LXPremium Knoop Hardness: 520

Stock sizes are available up to 48- x 96'. Available upon special request is 48"x102".

1.800.381.5335 | sales@marshield.com | www.marshield.com

LEAD LINED STORAGE CONTAINERS • MODULAR RADIATION BARRIERS & WALLS • MODULAR X-RAY ROOMS • ROLLING RADIATION BARRIERS • SHEET LEAD



SAFETY LEAD GLASS

*High Radiation Shielding in PET Scan Treatment
Pro-GR Radiation Shielding*

DESCRIPTION:

MarShield's Pro-GR radiation shielding glass is made of glass materials having a lead oxide content rate of roughly 70% that is equivalent to ultra-high lead content block glass for nuclear power facilities. Pro-GR has a radiation shielding capability higher than that of conventional LX-57B lead glass. It is commonly used to shield gamma rays (0.511 MeV) in PET facilities.

Pro-GR is Available for Timely Delivery and Long Lead Times are Avoided.

PRO - GR PRODUCT DATA		
THICKNESS (MM)	PRO-GR 14.7	PRO-GR 21.8
Lead Equivalent (mm)	5	7.5
Weight (lbs/ft ²)	15.8	23.5
Visible Light Transmission	83%	83%
Specific Gravity	Min. 5.20	Min. 5.20
Refractive Index	1.81	1.81
Maximum Size	1000 mm x 1500 mm (42" x 60")	

**Learn More About
Radiation Shielding**

1.800.381.5335 | sales@marshield.com | www.marshield.com

LEAD LINED STORAGE CONTAINERS • MODULAR RADIATION BARRIERS & WALLS • MODULAR X-RAY ROOMS • ROLLING RADIATION BARRIERS • SHEET LEAD